

STUDY ON PERVIOUS CONCRETE BY USING COST EFFECTIVE MATERIALS

Hemalatha .L¹, Keerthana .S², Jagadesh .P³, Karthik Prabhu .T⁴

^{1,2}PG Students, Department of Environmental Engineering and Management, Coimbatore Institute of Technology, Tamil Nadu, India.

³Assistant professor, Department of Civil Engineering, Coimbatore Institute of Technology, Tamil Nadu, India,

Abstract - The past decade of the construction world has shown vast interest in pervious concrete. The study focus is on the strength comparison eco-friendly pervious concrete by replacement of cost effective materials in pervious concrete. The effective utilization of waste recycles materials like fly ash, steel slag, rubber chips and silica fume will indirectly reduce environment pollution. The replacement for cement was done by 8% to 25% of fly ash and silica fume and for coarse aggregate by 2% to 30% of steel slag and rubber chips. Using the selected aggregates the strength of pervious concrete is improved economically. In the past few days flyash generation is more and it is used to increase the strength of the concrete world.

Key words: Pervious concrete, No fines, strength, porosity, Replacement.

1. INTRODUCTION

Pervious concrete is a special type of concrete made using coarse aggregates with little or no fine aggregate with carefully controlled amount of water and cementitious materials hence it called as 'no-fines concrete'. Pervious concrete is a zero-slump concrete having void content of about 15% to 25% and a have flow rate of 0.34 cm/second. Pervious concrete has a large open pore structure hence it has less heat storage and faster in flow characteristics. The paste coats and binds the aggregate particles together to create a system of highly permeable, interconnected voids that promote the rapid drainage of water. Pervious concrete is traditionally used in parking areas, areas with light traffic, residential streets, pedestrian walkways, and green houses. It is an important application for sustainable construction. Pervious concrete have high porosity used for concrete flat applications allows water from precipitation and other sources to pass directly through, thereby reducing the runoff from a site and allowing groundwater recharge. In India electricity demand has tremendously increased due to industrialization and rapid economic growth. Coal plays a major role in production of flyash and this will increase in future. India ranks fourth in production of coal ash in world level. In the year 2014, 777.1 Million tonnes of flyash was produced at world level in that 415.5 Million tonnes of flyash was utilized, rate of utilization is 53.5%

(Sirajuddin Ahmed et al). In the same year India's contribution in production of flyash is 184.14 Million tonnes and utilized is 102.54 Million tonnes and the utilization rate is 55.69%. In India the production rate is the generation rate is decreased in the year 2015-16 to 176.74 Million tonnes and the utilization rate is increased to 107.77 Million tonnes, the utilization rate is 60.79%. In the first half of 2016-17 the generation is 85.48 Million tonnes and utilized is 49.52 Million tonnes and the utilization rate is 57.93% (ENVIS Centre on Flyash). In current scenario the production steel slag is 12 Million tonnes in India (Indian mineral year book May 2016). Steel slag is used as recycled raw materials as road aggregate, cement and concrete admixture, soil stabilizer and construction materials etc, by its physical and chemical properties. The main objective of the project is to utilize the by-products from the production of steel and thermal power stations which are considered as waste residues as a replacement material in concrete thus to enable recycle process. The optimum percentage replacement of supplementary materials and industrial by-products helps in reduction of overall construction cost and also to play a major role in improvement of social and environmental standards in an eco-friendly manner.

2. MATERILAS AND THEIR PROPERTIES

53 grade OPC ensures better concrete properties and withstand other natural causes of Concrete deteriorations such as Sulphate and Alkali attacks as per IS:12269-1987 is selected. Coarse aggregate having maximum size of 20mm are used for the work. As per IS:2386-1963 ,Coarse aggregate is chosen. Fly ash can be used in Portland cement concrete to enhance the performance of the concrete. Fly ash has high pozzolans. Fly ah is selected as per ACI:318-08. The fly ash selected Class C. Silica fume is a by-product of production of silicon and ferrosilicon alloys. Silica fume is added to Portland cement concrete to improve its properties, compressive strength, bond strength and abrasion resistance. The quality of silica fume is specified by ASTM C 1240 and AASHTO M 307. The non-degradable nature of rubber and consequent disposal problem has led to a serious environmental issue in the recent decades. Using this waste materials in concrete can solve these problem. Tires are from MRF brand are chosen. Replacement of Steel Slag is done for both coarse

4.2. Anova analysis

SUMMARY							
Groups	Count	Sum	Mean	Variance	Standard Deviation	Low	High
COMPRESSIVE STRENGTH	23	324.59	14.11261	20.7239929	4.552361243	9.56024745	18.66497
FLEXURAL STRENGTH	23	78.97	3.433478	0.99336008	0.99667451	2.43680375	4.4301528
SPLIT TENSILE STRENGTH	23	31.3	1.36087	0.19281739	0.439109771	0.92175979	1.7999793

ANOVA						
Source of Variation	SS	df	MS	F	P-value	F crit
Between Groups	2153.922	2	1076.961	147.460443	4.47047E-25	3.13591793
Within Groups	482.0237	66	7.30339			
Total	2635.946	68				

Fig-1: Anova analysis of strength of concrete

Where,

SS- Sum of square

df- Degree of freedom

MS- Mean square

F- Critical value

MS=Mean square between group/mean square within the group

df=K-1 (between groups)

df=K(n-1) (within group)

n= Total column value

5. CONCLUSION

The summary of the conclusion is based on experimental and analytical study on conventional rigid concrete and pervious rigid concrete.

1. With the replacement of flyash for a portion of cement increases the compressive strength to some extent and it will decrease with the increase in flyash.
2. The silica fume plays act as good reactive pozzolan, as per our result silica fume increases the mechanical properties of pervious concrete.
3. With the increase in steel slag at 6% increases the compressive strength. Usage of steel slag instead of natural aggregates avoids the environmental footprint of quarrying, and also prevents deforestation.

4. T3 mix with replacements by 10% silica fume and 4% steel slag gives the highest flexural strength.
5. Addition of rubber waste increases the split tensile strength. Increase in rubber percentage increases the split tensile strength to some extent. The rubber of 2% replacement gave the highest split tensile strength.
6. Thus as per our study flyash is widely used as concrete material. The mechanical strength of pervious concrete is increased by replacements of waste materials for cement and coarse aggregate
7. The carbon footprints has drastically decreased by replacements for cement.
8. It is observed that the cost of construction of our pervious concrete mix is decreased by 27% as compared when super plastizers are used.

REFERENCES

1. National Ready Mixed Concrete Association (2004), 'Freeze-Thaw resistance of pervious concrete'.
2. Richard c Meininger, 'No Fines Pervious Concrete for Paving', Concrete International Vol. 10, No. 8, August 1988, pp. 391-399.
3. Matthew Offenber(2005), 'Producing pervious pavements', Concrete International, Vol.27 , pp.50-53.
4. Maslehuddin, Alfarabi, Ibrahim, Barry (2003), 'Comparison of properties of steel slag and crushed limestone aggregate concrete', Construction and Building Materials, Vol.72, pp42-47.
5. B.B.Kar, S Dash, T. Panda, S.M. Mustakim "Treatment of fly ash to produce efficient concrete material" , International Journal of Innovative Research in Science, Engineering and Technology, ISSN: 2319-8753, Vol. 2, Issue 8, August 2013
6. IRC 58-1988 Guidelines for Design of Rigid pavements for Highways.
7. IS 10262-2009 'IS Method of Mix Design', Bureau of Indian Standards, New Delhi, India.
8. IS 12269-1989, "Specification for 53 grade ordinary Portland cement", Bureau of Indian Standards, New Delhi, India.

9. IS 383-1970, 'Specification for coarse and fine aggregate from natural sources for concrete, Bureau of Indian Standards', New Delhi, India.
10. IS 516-1959, 'Methods of tests for strength of concrete, Bureau of Indian Standards', New Delhi, India.
11. IS 2386 (Part 1)-1963, 'Methods of test for aggregates for concrete; particle size and shape', Bureau of Indian Standards, New Delhi.
12. IRC 44-1976 Tentative guidelines for cement concrete mix design for pavements.
13. Babu (1993), "Behaviour of lightweight expanded polystyrene concrete containing silica fume", Cement and Concrete Research, Vol. 51, pp 71-75.
14. Durability of pervious concrete using crushed seashells Dang Hanh Nguyen a,b,† , Mohamed Boutouil b , Nassim Sebaibi b , Fabienne Baraud c , Lydia Leleyter.
15. Experimental Study on Mechanical and Hydrological Properties of Pervious Concrete with Different Water Cement Ratio.
16. Dash, S.K and Kar, B.B, "Preparation of water absorbing pavement material from fly ash", Asian Journal of water and environmental protection-AJWEP/082/130313.
17. S.K.Dash, B.B Kar, P.S Mukherjee, S.M. Mustakim "Effect of organic binders on properties of Fly ash aggregate".
18. Flexural Strength Behaviour of Pervious Concrete Using Fibre and Mineral Admixtures BHUVANESH K V 1 , SREEVIDYA V 1 , HEMA S 1 AND M VADIVEL 2 1Department of Civil Engineering, Sri Krishna College of Technology, India 2Department of Civil Engineering, Nehru Institute of Technology, INDIA.
19. Experimental Study of Pervious Concrete Pavement Vikram 1 , Mahla R.P.*2 1 M. Tech Student, Department of Civil Engineering, OITM/GJU- Hisar (125001), Haryana, India 2 Department of Civil Engineering, OITM/GJU- Hisar (125001), Haryana, India.
20. Tech Brief ACPT DECEMBER 2012 | FHWA-HIF-13-006.
21. <http://www.perviouspavement.org/engineering.html>.
22. Pervious Concrete: Mix Design, Properties and Applications Mohammed Sonebia*, Mohamed Bassuonib , Ammar Yahiac.
23. A review on performance of pervious concrete using waste materials Sukamal Kanta Ghosh 1 , Ananya Chaudhury 2 , Rohan Datta 3 , D.K.Bera 4
24. Properties of Cement Mortar Containing Rubber Ash as Sand Replacement <http://iopscience.iop.org>
25. https://www.researchgate.net/publication/306401384_Performance_Assessment_of_Pervious_Concrete_by_Using_Silica_Fume.
26. The effect of silica fume on the properties of concrete as defined in concrete society report 74, cementitious materials Des King Hon. FICT, Dip M, Chartered MCIM, DMS Consultant, United Kingdom.
27. Experimental investigation of pervious concrete with use of fly ash and silica fume as admixture A.A.Haji 1, Dr.K.B.Parikh 2, M.A.Shaikh 3, M.A.Jamnu 4.
28. Tyre rubber wastes based concrete: a review. F.Pacheco Torgal 1 , A. Shasavandi 2 and S. Jalali 3.
29. Influence of Fly Ash and Fine Aggregates on the Characteristics of Pervious Concrete Uma Magesvari, M*, 1 and Sundararajan, T*, 2 * - Dept. of Civil Engineering, Pondicherry Engineering College, Pondicherry-605014, India. 1Corresponding author.
30. Mix design for pervious recycled aggregate concrete –International journal of concrete structures and materials.

BIOGRAPHIES



"Hemalatha.L is a PG scholar in the stream of Environmental Engineering and Management in Coimbatore Institute of Technology, She completed her UG in the stream of Civil Engineering in SriGuru Institute of Technology. She is pursuing her first year."



"Keerthana.is a PG scholar in the stream of Environmental Engineering and Management in Coimbatore Institute of Technology, She completed her UG in the stream of Civil Engineering in Dhanalakshmi Srinivasan Engineering College . She is pursuing her first year."



"Jagadesh.P is currently working as an assistant professor at Department of civil engineering in Coimbatore Institute of Technology."



"Karthik Prabhu.T is an assistant professor at Department of civil engineering in Coimbatore Institute of Technology."