

# AN INVESTIGATION ON MECHANICAL AND DURABILITY OF SELF COMPACTING CONCRETE

KU. Mani Kandhan<sup>1</sup>, T. Sri Vishnu<sup>2</sup>

<sup>1</sup>Associate Professor, Department of Civil Engineering, Nandha Engineering College, Erode.

<sup>2</sup>M.Tech Student, Department of Civil Engineering, Nandha Engineering College, Erode.

\*\*\*

**Abstract** - Concrete are the most important materials used in construction industries where the external forces more than design loads mainly the lateral forces which leads to the deformation and produce cracks in the joints of the structural member. The usage of cement has been increased more over the worlds results in the air pollution which leads to the ozone depletion. Self Compacting concrete get dense and compacted due to its own self-weight. An experimental investigation has been carried to determine the durability and mechanical properties of the Self -Compacting concrete Comparison between EFNARC and IS Codal provision with Mix Design proportions for a particular mix of SCC. Test methods used to study the properties of fresh concrete were slump test, U- test, V- funnel and L – Box test. Compare of EFNARC and IS Standard with various Viscosity Modifying Admixtures like Glenium Stream 2, Auramix, Poly Ethylene Glycos(PEG). With various percentage of addition to make which one give better strength between them all.

SCC is sensibly utilized, the reduced of costs caused by better productivity, shorter construction time and improved working conditions will compensate the higher material costs and in many cases, may result in more favorable prizes of the final

## 1.1 SELF COMPACTING CONCRETE

Self Compacting concrete was first developed in japan around the year 1980. Professor H. Okamura from the university of Tokyo is mainly responsible for initiating the development of such concrete. Self Compacting concrete also referred to as Self Consolidation Concrete or silent concrete can be considered as the greatest technical advancement and most today. This is the concrete for the future. It is reported in the year 2003 approximately 50% of total concrete executed in japan is self compacting concrete. In India it was used for the first time in the year 2003 and the work was executed by Gammon India Ltd.

**Key Words:** Self compacting concrete, EFNARC, IS, VMA, HRWR.

## 1. INTRODUCTION

Self-compacting concrete (SCC) represents one of the most outstanding advances in concrete technology during the last decade. At first developed in japan in the late 1980, SCC meanwhile is spread all over the world with steadily increasing number of application. Due to its specific properties, SCC may contribute to a significant improvement of the quality of concrete structure and open up new fields for the application of concrete. SCC describes a concrete with the ability to compact itself only by means of its own weight without requirement of vibration. It fills all recesses, reinforcement spaces and voids, even in highly reinforced concrete members and flows free of segregation nearly to level balance. While flowing in the formwork, SCC is able to deaerate almost completely. The use of SCC offers many benefits to the construction practice the elimination of the compaction work results in reduced in costs of placement, a shortening of the construction time and therefore in an productivity. The application of SCC also leads to a reduction of noise during casting, better working conditions and the possibility of expanding the placing times in inner city areas. Other advantages of SCC are an improved homogeneity of the concrete production and the excellent surface quality without blowholes or other surface defects. Often the materials costs of SCC will be higher than he equivalent material costs of a normal vibrated concrete however, when

This type of concrete was first propose by Okamura in 1986. The motivation behind this was the gradual reduction of skilled workers in Japan's construction industry which led to a reduction in the quality of construction work. This further, affected adversely the durability of concrete that has been poorly compacted. SCC was developed to counter the problems of compaction and associated poor quality of concrete. It is basically a high flowable concrete. When the construction industry in japan experienced a decline in the availability of skilled labor in the 1980's a need was felt for a concrete that would overcome the problems of defective workmanship. This led to a development of self compacting concrete, primarily through the work of Okamura. Data indicate that the share of application of SCC, in pre cast concrete industry is more than three times than that in the ready-mixed concrete industry. This is attributed to the higher cost of SCC. The estimated average price of SCC supplied by RMC industry in japan was 1.5 times that of the conventional concrete in the year 2002, such as in lattice type structures, casting without pump, and tunnel linings. It was developed in order to overcome the following problems in conventional concrete construction:

- Improper consolidation of inaccessible of inaccessible area (deep lying or in zones of congested reinforcement) it can ensure quality.
- Tremendous waste of energy in vibration – based compaction. 21

- Vibration-related hearing loss and other injuries to workers.

## 2. REVIEW WORKS

**Payal Painuly: Making** concrete structure without compaction has been done in the past. Like placement of concrete underwater by the use of termie without compaction. Inaccessible areas were concreted using such techniques. The production of such mixes often used expensive admixtures and very large quantity of cement. But such concrete was generally of lower strength and difficult to obtain. This lead to the development of Self Compacting Concrete (SCC) The workability properties of SCC such as filling ability, passing ability and segregation resistance are evaluated using workability tests such as slump flow, V-funnel and L-Box tests.

**Mr. Anup Panusuria:** Concrete is a family of binding material, fine aggregate, coarse aggregate and water. Concrete is normally used in the frame structure. But there is some limitation like self-compaction, surface finishes, maintains strength at congested area. Due to this limitation we are trying to make self-compacting concrete with the use of mineral admixture. SCC is concrete that can be placed and compacted under its own weight without any vibration effort, assuring complete filling of formwork even when access is hindered by narrow gaps between reinforcement bars. The primary objective of this study is to make use of Ground granulated blast furnace slag (GGBS) as a replacement of cement and understand its effects on the fresh properties, compressive strength weathering. The study also intended to quantify the amount of Ground granulated blast furnace slag (GGBS) to be added to the concrete according to the value of concrete properties Measured. The workability of self-compacted concrete is increased as content of GGBS increased. Compressive strength of SCC with GGBS is increased up to 10% replacement of cement with GGBS.

**Guru Jawahar:** This paper investigated the use of mini slump cone test along with the graduated glass plate to obtain the optimization of Superplasticizer (SP) and Viscosity Modifying Agent (VMA) in self compacting mortar (SCM). The SCM mixes had 35% replacement of cement with class F fly ash and water/cementitious ratios by weight (w/cm) 0.32 and 0.36. It is observed that for the same cementitious proportions, the optimum dosage of SP was the same for the mixes having w/cm 0.32 and 0.36. Mortar mixes with w/cm 0.36 showed an increase in the rate of flow i.e., lower viscosity at each level of SP dosage as compared to that of mixes with w/cm 0.32. It is also observed that minimum dosage of VMA was required to use in the mortar mixes having w/cm 0.36 in order to arrest the bleeding. Whereas, the use of VMA dosage was not required to use in the mortar mixes having w/cm 0.32 as no bleeding was observed at the optimum dosage of SP. Practically, it is seen that mini slump cone test is the best choice for SCM tests to evaluate the mortar spread and its viscosity (T<sub>20</sub>). Also, it is

seen that percentage of sand in mortar doesn't affect the optimum dosage of SP (saturation point) when the cementitious proportions are kept the same.

## 3. CONCLUSIONS

- I. In spite of its short history, self compacting concrete has confirmed itself as a revolutionary step forward in concrete technology.
- II. Due to observed workability and high flow ability of SCC, it can be used in highly congested reinforcement structure as compare to conventional concrete.
- III. Since in the near future service life design (SLD) of concrete structures will be as important as design for safety and serviceability, increased attention should be given to the role of the microstructure of the various types of available SCC's and its role for durability.
- IV. Besides, from the review of literatures related to SCC which I have gone through, have got an literal facts and objectives about the SCC- Mix design based on EFNARC-2005(revised edition) and IS : 10262 – 2019(revised edition) and types of VMA based on EFNARC – 2006(revised edition).
- V. So, in the forthcoming project work, I have planned to experiment the SCC in the min proportions of M<sub>50</sub> Grade in EFNARC and IS codal provisions and compare their mechanical and durability proportions by casting the framed members like beams & slabs etc.,
- VI. Due to its high observing factors related to workability we have to choose the VMA(EFNARC-2006 (revised edition)) based upon their reliability and their ability to flow among the concrete.

From all the above gathered literatures and journals. We got same idea related about Self compacting concrete and learned the way of designing a self compacting concrete and way of proportion of mix design.

Above literatures and journals related with separate preparation of EFNARC and IS codal provision. It gives a results of production of self compacting concrete.

The role of the project, Study and comparison of Self compacting concrete from EFNARC and IS Provision from revised standard of EFNARC: May 2005 and IS : 2019 Edition. Comparing of Viscosity Modifying Admixtures (VMA) with this provision.

While the project completion. We can able to find which codal provision is better and suitable for making a self compacting concrete all form factors.

**REFERENCES**

- [1] EFNARC - The European guidelines for self-compacting concrete, Specification, Production and Use, 2005.
- [2] IS 10262-2004, Recommended guidelines for concrete mix design, Bureau of Indian Standards, New Delhi, India.
- [3] IS: 1489 (Part-I)-2015, Portland - Pozzolana cement specification, Bureau of Indian Standards, New Delhi, India.
- [4] IS: 9103, Indian Standard for Concrete Admixtures-Specification, Bureau of Indian Standards, New Delhi, India, 1999.
- [5] IS: 456-2000, Code of practice for plain and reinforced concrete, Bureau of Indian Standards, New Delhi, India.
- [6] Payal Painuly, Literature Review On Self Compacting Concrete, international journal of technical research and application vol no 04, issue no 2, (March - April,2016)PP.178-180.
- [7] Mr. Anup Panusuria, Literature Review On Role Vma In Concrete, IJARIE-ISSN(O)-2395-4396 vol no 03, issue no 5, 2017.
- [8] Guru Jawahar, Optimization Of Superplasticizer And Viscosity Modifying Agent In Self Compacting Mortar, Asian journal of civil engineering(BHRC) vol no 14, issue no 1(2013),PP 71-86.
- [9] K. Elissa, "Title of paper if known," unpublished.