

STUDY ON BEHAVIOUR AND DURABILITY PROPERTIES OF CONCRETE AND MORTAR BY THE INFLUENCE OF LIME AS PARTIAL REPLACEMENT OF CEMENT

KU. MANI KANDHAN¹, V.K. KARUNAKARAN²

¹ Assistant Professor, Department of Civil Engineering, Nandha Engineering College, Tamilnadu, India

² PG Student, Department of Civil Engineering, Nandha Engineering College, Tamilnadu, India

Abstract: The present paper has investigated the compressive strength and shear bond strength behaviour of hydraulic lime cement concrete and mortar. Concrete of M-30 was made using Ordinary Portland cement, which was partially replaced by hydraulic lime at varying percentages ranging from 0% to 100% in concrete and 0% to 100% in mortar. There is critical issue with this type of cement replacement i.e. the change in physical properties of concrete and mortar. This research looks at the change in physical properties of concrete when cement is replaced by lime with respect to compressive strength in concrete and shear bond strength in mortar. The results from this research study show a linear diminution in strength with linear increase in the relative % age of lime to cement. The shear bond strength of triplet specimen was increased with increase in lime content in mortar. The compressive strength of lime concrete cube specimens were increases when the replacement of lime up to 15% and with higher percentage, strength decreases considerably.

Key Words: Lime concrete, Lime mortar, Compressive strength, Shear bond strength etc.,

1 INTRODUCTION

1.1 General

An artificially built up stone hardening of a mixture of cement, sand, aggregates and water with or without a suitable admixture, is generally known as "concrete". Concrete is used for made of building components like beam, column, slab etc. Mortar is mixture of cement, sand and water which is used to bind bricks or stones in wall of buildings, plaster on walls, concrete masonry units. Mostly concrete and mortar are made with cement but sometimes cement replace by few amount of other admixture like hydraulic lime, fly ash, red mud, silica fume, glass etc. to enhancement of mechanical properties of concrete and mortar. These properties are such as compressive, tensile, flexure and shear bond strength etc. Lime is used as the primary binder in many mixes such as a lime putty or hydraulic lime. Lime is a durable, abundant and versatile binder that has been used extensively in construction like Lime concrete, lime mortar etc. for thousands of years. Lime is calcium containing inorganic material in which carbonates, oxides and hydroxides predominate. It is derived from limestone or chalk. They may be crushed, cut or pulverized and chemically altered. Lime improves the workability, plasticity, cohesion, adhesion, air content and

water content. Broadly lime is classified into three categories fat lime, hydraulic lime, poor lime etc. In this study, they have to use the hydraulic lime as admixture by replacement of cement in concrete and mortar. Hydraulic lime has hydraulic property so it can set under water and it is also known as water lime. Natural hydraulic lime is made from a limestone which naturally contains some clay. Artificial hydraulic lime is made by adding forms of silica and alumina such as clay to the limestone during firing, or by adding a pozzolana to pure lime. Hydraulic lime are classified by their strength, moderately and eminently lime. It contains some amount of ferrous oxide and clays also. Depending upon the clay particle it may be further divided into following categories (a) Eminently hydraulic (b) Semi hydraulic (c) Non hydraulic lime. Mostly hydraulic lime is used for mortar and plaster. Concrete's compressive strength mostly depends on the concrete mix design. It is also affected by other factors such as mixing of concrete, placing of concrete, curing of concrete as well as quality of concrete ingredients. Compressive strength is the maximum compressive stress that, under a gradually applied load, a given solid material can sustain without fracture. Measurements of compressive strength are affected by the specific test methods and conditions of measurements. The shear bond strength in masonry is the force in shear required to separate the units from the mortar. The shear bond strength is the bond strength between the brick mortar and interface of brick. The bond development in masonry is on account of mechanical interlocking of hydrated cement product into the pores of the bricks.

1.2 OBJECTIVES

The aim of the investigation is to investigate the behavior and durability properties of concrete and mortar by the influence of lime as partial replacement of cement.

1.3 SCOPE

- The scope of the present investigation can be summarized as follows:
- To study the effect of behaviour and durability properties of concrete and mortar with there placement of cement by lime powder.
- To achieve 28 days characteristic compressive strength of 30 MPa.
- To compare the variation of compressive strength at 7 days ,14 days and 28 days strength between normal concrete and lime concrete.

- In the present investigation more emphasis is given to study the lime concrete. So as to achieve better concrete composite and to encourage the use of lime to overcome the environmental impacts caused cement.

2 LITERATURE REVIEW

A Costigan et al. (A & S, 2009) discussed the strength behaviour of hydraulic and non-hydraulic lime mortars in clay brick masonry bond. They used two masonry types under lateral and vertical load. Authors concluded that compressive and flexural strength of NHL5 mortar increases by 60-65% between 28 days and 56 days while its flexural bond strength increases by 80%. However, the compressive strength of the NHL5 bound masonry only increases by 11%, after 56 days the NHL 5 mortar is stronger in compression than the NHL5 masonry whereas the CL90-s mortar / masonry shows the opposite trend.

C. Freeda Christy et al. (Christy, Shanthi, & D. Tensing, 2012) investigated shear bond strength of small burnt clay brick masonry samples. They have been received shear bond strength from three brick triplets. In this paper, the authors concluded that © 2019 JETIR May 2019, Volume 6, Issue 5 www.jetir.org (ISSN-2349-5162) JETIR1905K43 Journal of Emerging Technologies and Innovative Research (JETIR) www.jetir.org 327 shear bond strength of unreinforced clay brick masonry in the ratio of 1:6 cement mortar with 20% replacement of fine aggregate with fly ash was 1.45 times more than the unreinforced clay brick masonry in the ratio of 1:6 cement mortar, shear bond strength of reinforced clay brick masonry in the ratio of 1:6 cement mortar with 20% replacement of fine aggregate with fly ash was 1.5 times more than the unreinforced clay brick masonry, shear bond strength of reinforced fly ash brick masonry in the ratio of 1:6 cement mortar with 10% replacement of fine aggregate with fly ash was twice than the unreinforced fly ash brick masonry.

Awodiji Chioma Temitope Gloria et al. (Gloria, Ogbonnaya, & Olujide, 2017) investigated the flexural strength and tensile strength of hydrated lime cement Concrete. In the present study, they used hydrated lime replace by cement from 5% to 30%. Authors concluded that the highest flexural strength and tensile strength at 13.83% replacement of hydrated lime by cement in concrete for 28 days of curing, flexural strength higher than split tensile strength of concrete.

N. Suneel et al. (Kumar N., Kumar, M. Thirupathamma, D. Sasikala, & Sarada, 2017) discussed the experimental study of concrete strength when cement replace by lime powder from 0% to 30%. They used M-20 grade of concrete for study. In this study, the authors concluded that compressive and tensile strength is maximum on 30% replacement of cement by lime with high workability.

Dr. A. Anbuchejian et al. (A. Anbuchejian & Kumar, 2018) discussed experimental work on Split Tensile Strength, Flexural Strength and Compressive Strength of concrete. They used groundnut shell replacement of fine aggregate and lime powder replacement of cement in concrete. In this paper, the authors have been partially changed fine aggregate as groundnut shell in the percentage of 5,10,15,20 and lime powder partly replaced in general ratio of 20 percentages. They concluded that groundnut shell concrete achieves more strength at 5% to 10% than normal concrete and lime concrete achieve more strength at 20% than normal concrete.

B. T. Sapna et al. (B. T. Sapna & M. Aravindhraj, 2018) discussed the compressive, split tensile, flexural strength of concrete when cement replaced by 0%, 5%, 10%, 15%, 20% of red mud and 5% hydrated lime. They concluded that compressive strength of the concrete achieved up to 17% for the replacement of red mud with cement by 15% and 5% of hydrated lime compared to normal concrete, split tensile strength of concrete achieved up to 23% replacement of red mud with cement by 15% and 5% of hydrated lime compared to normal concrete, the Authors saw that compressive strength of cubes and split tensile strengths of cylinder the optimum percentage of replacement of red mud with cement was 15% and 5% of hydrated lime.

S. Pavia et al. (Pavia & R. Hanley, 2010) measured flexural bond strength of natural hydraulic lime mortar (NHL) with mortar hydraulicity, water content, workability and water retention. They concluded that NHL5 mortar strongest bond with medium flow concurrently providing the highest water retention and best workability. However, NHL 2 and NHL 3.5 mortars are achieve lower bond strength with optimum workability but it is the highest flow values that provide the NHL2 and NHL3.5 mortars with the strongest bond comparison to other.

In this Chapter an elaborate discussion is made regarding works done so far in this area as literature review. Going to study about the behavior and durability properties of concrete and mortar by the influence of lime as partial replacement of cement.

3. PROPERTIES OF LIME IN CONCRETE

Lime concrete provides good bases to bear the sufficient loads and also provide certain degree of flexibility. It adjusts very well when it is in contact with surface. Lime concrete also exhibits certain degree of water proofing property and thus prevents subsoil dampness in floors and walls. Lime concrete also exhibits volumetric stability. It can be made easily and can be available at much cheaper rates. It also resists weathering effects and is very durable. Lime is one of the oldest binding materials used in several ancient architectural works. A good quality lime should own the following properties:

- It should possess good plasticity.

- It should be flexible and easily workable.
- When used in mortar, it should provide greater strength to the masonry.
- It should solidify in less time and become hard.
- It should comprise of excellent binding properties which adhere to brick or stone masonry units perfectly.
- It possesses high durable properties as it is less shrinkable when used in mortar.

It should be highly resistant to moisture and can be used for pointing works

3.1 DIFFERENCE BETWEEN LIME AND CEMENT

3.1.1 CHEMICAL COMPOSITION

Lime is produced from natural limestone by burning the stone in a kiln until only quicklime calcium oxide is left behind. The quicklime is then mixed with small amounts of water to create hydrated lime, which may be included in cement or mixed with water for use as mortar. Lime hardens by slowly absorbing carbon dioxide and turning back to limestone over time. Cement consists of highly reactive silica-containing compounds when mixed with water, they harden quickly.

3.1.2 PHYSICAL PROPERTIES

Lime hardens much more slowly than cement-containing mortars, making it much more workable. Lime is also less brittle and less prone to cracking, and any cracked areas can absorb carbon dioxide and mend over time. Cement hardens very quickly, but may be too strong for some applications, e.g., working with old bricks. Cement is also prone to cracking as a structure settles, and may eventually require repair.

3.1.3 VAPOR BARRIER

Lime is also breathable, allowing vapours to pass through, which can reduce moisture and improve the environment of the home. Cement creates a waterproof barrier that does not allow vapours to escape, and can absorb water, causing moisture to accumulate -- especially in basements.

3.1.4 ENVIRONMENTAL CONCERNS

Lime production results in release of carbon dioxide into the atmosphere, but lime mortar absorbs carbon dioxide from the atmosphere over its lifetime. As a result, lime mortar is considered by environmentalists to be "carbon neutral." In contrast, cement production contributes greatly to global warming, as copious amounts of carbon dioxide are released during its production.

3.2 LIME MORTAR :

Lime mortar is composed of lime and an aggregate such as sand, mixed with water. The Ancient Egyptians were the first to use lime mortars. Which they used to plaster the pyramids at Giza. In addition, the Egyptians also incorporated various limes into their religious temples as well as their homes. Indian traditional structures built with lime mortar, which are more than 4,000 years old like Mohenjo-darois still a heritage monument of Indus valley civilization in Pakistan. It is one of the oldest known types of mortar also used in ancient Rome and Greece, when it largely replaced the clay and gypsum mortars common to ancient Egyptian construction. With the introduction of Portland cement during the 19th century, the use of lime mortar in new constructions gradually declined. This was largely due to the ease of use of Portland cement, its quick setting, and high compressive strength. However, the soft and porous properties of lime mortar provide certain advantages when working with softer building materials such as natural stone and terracotta. For this reason, while Portland cement continues to be commonly used in new constructions of brick and concrete construction, in the repair and restoration of brick and stone-built structures originally built using lime mortar, the use of Portland cement is not recommended. Despite its enduring utility over many centuries, lime mortar's effectiveness as a building material has not been well understood; time-honoured practices were based on tradition, folklore and trade knowledge, vindicated by the vast number of old buildings that remain standing. Only during the last few decades has empirical testing provided a scientific understanding of its remarkable durability. Both professionals and do-it-yourself homeowners can purchase lime putty mortar (and have their historical mortar matched for both color and content) by companies that specialize in historical preservation and sell pre-mixed mortar in small batches.

4. MATERIALS TO BE USED

4.1 CEMENT

Cement is a binder, a substance used for construction that sets, hardens, and adheres to other materials to bind them together. Cement is seldom used on its own, but rather to bind sand and gravel (aggregate) together. Cement mixed with fine aggregate produces mortar for masonry, or with sand and gravel, produces concrete. Concrete is the most widely used material in existence and is only behind water as the planet's most-consumed resource.

4.2 M-SAND

Manufactured is an alternative for river sand. Due to fast growing construction industry, the demand for sand has increased tremendously, causing deficiency of river sand in

most part of the world. Due to depletion of good quality river sand for the use of construction, the use of manufactured sand has been increased. Another reason for use of M Sand is its availability and transportation cost.

4.3 COARSE AGGREGATE

Coarse aggregate is mined from rock quarries or dredged from river beds, therefore the size, shape, hardness, texture and many other properties can vary greatly based on location. Even materials coming from the same quarry or pit and type of stone can vary greatly. Most generally, coarse aggregate can be characterized as either smooth or rounded (such as river gravel) or angular (such as crushed stone).

4.4 LIME

Lime is a calcium-containing inorganic mineral composed primarily of oxides, and hydroxide, usually calcium oxide and/ or calcium hydroxide. It is also the name for calcium oxide which occurs as a product of coal-seam fires and in altered limestone xenoliths in volcanic ejecta. The word lime originates with its earliest use as building mortar and has the sense of sticking or adhering. These materials are still used in large quantities as building and engineering materials (including limestone products, cement, concrete, and mortar), as chemical feedstocks, and for sugar refining, among other uses. Lime industries and the use of many of the resulting products date from prehistoric times in both the Old World and the New World. Lime is used extensively for wastewater treatment with ferrous sulfate. The rocks and minerals from which these materials are derived, typically limestone or chalk, are composed primarily of calcium carbonate. They may be cut, crushed, or pulverized and chemically altered. Burning (calcination) of these minerals in a lime kiln converts them into the highly caustic material burnt lime, unslaked lime or quicklime (calcium oxide) and, through subsequent addition of water, into the less caustic (but still strongly alkaline) slaked lime or hydrated lime (calcium hydroxide, $\text{Ca}(\text{OH})_2$), the process of which is called slaking of lime. When the term is encountered in an agricultural context, it usually refers to agricultural lime, which today is usually crushed limestone, not a product of a lime kiln. Otherwise it most commonly means slaked lime, as the more dangerous form is usually described more specifically as quicklime or burnt lime

5. TESTS TO BE CONDUCTED

Fresh concrete tests such as Slump cone test, L-Box test, V-Funnel test are to be performed. Compressive strength test, Split tensile test and Flexural strength and Shear bond test are also proposed to be conducted. Mix designs are arrived by using IS 10262-2019

6. CONCLUSIONS

From the above journal it is evident that High Strength Concrete plays a vital role in construction industry. In

addition to that the Lime is added in concrete to attain good plasticity, workability and durability and work has been done.

REFERENCES

1. "STUDY ON THE PERFORMANCE ENHANCEMENT OF LIME MORTAR" Venugopal.B et.al., international journal of engineering research & technology vol no: 06 PECTEAM -2K18 conference proceedings.
2. "IMPACT ON COMPRESSIVE STRENGTH OF CONCRETE BY REPLACEMENT OF CEMENT WITH LIME POWDER" Prashant et.al., International Research Journal of Engineering and Technology (IRJET) vol-06 apr 2019.
3. "REPLACEMENT OF CEMENT BY LIME POWDER" N Suneel Kumar et.al., International Journal & Magazine of Engineering & Technology vol-04 (2017) ISSN NO : 2348-4845.
4. "FLEXURAL AND SPLIT TENSILE STRENGTH PROPERTIES OF LIME CEMENT CONCRETE" Awodiji Chioma Temitope Gloria et.al., Civil and Environmental Research vol- 09(2017) no; 3 ISSN 2224-5790.
5. "FLEXURAL BOND STRENGTH OF NATURAL HYDRAULIC LIME MORTAR AND CLAY BRICK" s.pavia et.al., material and structures (2010) 43:913-922.
6. "CONCRETE RE-INVESTIGATION OF THE COMPRESSIVESTRENGTH OF ORDINARY PORTLAND CEMENT CONCRETE AND LIME" Awodiji. C.T.G et.al., International Journal of Geology, Agriculture and Environmental Sciences ISSN: 2348-0254 Vol 04(2016).
7. "MECHANICAL PERFORMANCE OF LIME-CEMENT MORTAR FOR STRAW-BALE CONSTRUCTION" Colin MacDougall et.al., International Journal of Green Building, Vol.09, No. 3.
8. "THE INFLUENCE OF CEMENT ON PROPERTIES OF LIME MORTARS" L.Gulbeet et.al., Modern Building Material, Structures and Techniques, MBMST 2016s, Procedia Engineering 172 (2017) 325 – 332.
9. "THE MECHANICAL PROPERTIES OF LIME CONCRETE"Dr. Mohammed Mosleh Salman, et.al., Journal of Engineering and Sustainable Development Vol. 21, No. 02, March 2017.
10. "COMPRESSIVE STRENGTHS AND BOND STRENGTHS OF PORTLAND CEMENT-LIME MORTARS" J. Melander and L. Lauersdorf et.al., (West Conshohocken, PA: ASTM International, 1993), 105-120.